



FISA TEHNICA

DUROFLOOR

DATA SHEET

PRIMER

DESCRIERE:

DUROFLOOR PRIMER este un primer epoxidic, cu poliamida tratata, format din doua componente (A si B).

Este folosit ca strat initial in protejarea suprafetelor de vopsire expuse la conditii atmosferice. Prezinta rezistenta buna la chimicale si diferite impacturi. Se foloseste pardoselile din cladiri de birouri, depozite, hale industriale, spatii publice si comerciale, unitati de invatamant.

UTILIZARI:

Ca strat initial pentru suprafetele de vopsire, asigurand protejarea indelungata a pardoselilor. Inainte de aplicare, pardoselile trebuie sa fie curate, fara impuritati si urme de vopsea veche.

CONDITII DE UTILIZARE:

Suprafata de acoperire: 5-7 m²/kg (A + B)

Pellicula uscata: 80-125 µm.

Mod de utilizare: se amesteca bine partile A si B in proportie (pe greutate) A=1, B=1; se foloseste diluantul potrivit : DILUACHROM T – max 15%. Se aplica cu pensula, trafalet sau spray la temperatura cuprinse intre 13⁰C – 30⁰C si umiditate de max. 80%.

Valabil dupa amestecare: 6-10 ore.

DESCRIPTION:

DUROFLOOR PRIMER is an epoxy, anti-corrosion primer with treated polyamide, consisting of two components (A and B). It is used as an initial layer in protecting exposed paint surfaces from atmospheric conditions. It shows good resistance to chemicals and various impacts. Floors are used in office buildings, warehouses, industrial halls, public and commercial spaces, educational units.

USES:

As an initial coating for painting surfaces, providing long-lasting protection for boats and boats made of fiberglass and wood. Prior to application, the body of the boat must be clean, free of impurities and traces of old paint.

USAGE CONDITIONS:

Coverage area: 5-7 m² / kg (A + B)

Dry film: 80-125 µm.

Usage: thoroughly mix parts A and B in proportion (by weight) A = 1, B = 1; use the appropriate diluent: DILUACHROM



PRODUCĂTOR/ PRODUCER:
S.C. COSTHEVA S.R.L. - CHEMICALS - GASES - PAINTS
STR. CAPITAN PAPADOPOL NR. 14
CONSTANTA, ROMANIA
Tel.: 0241.62.54.05
office@costheva.com www.costheva.com



Timp de uscare (la 20-25⁰ C):

La suprafata: 4 ore/pe
revopsire: 4 ore – 7 zile/uscare finala: 7 zile.

Se aplica ulterior DUROFLOOR COAT.

ATENȚIE: Stratul final de vopsea dupa DUROFLOOR PRIMER se aplica dupa minim 4 ore si max. 7 zile.

TERMEN DE VALABILITATE: 12 luni de la data fabricației înscrisă pe ambalaj în condițiile respectării prevederilor de depozitare. A se depozita in spatii ferite de foc, inghet si de actiunea directa a razelor solare.

Produs realizat în sistem de management integrat al calitate - mediu - sănătate și securitate operațională în conformitate cu ISO 9001 / 2018, 14001 / 2018 și OHSAS 18001 / 2018.

Fraze de pericol si precautii: H315 - Provoacă iritarea pielii. Skin Sens. 1: H317 - Poate provoca o reacție alergică a pielii. H373 - Poate provoca leziuni ale organelor în caz de expunere prelungită sau repetată. H361d - Susceptibil de a dăuna fătului. H412 - Nociv pentru viața acvatică, cu efecte pe termen lung. H304 - Poate fi mortal în caz de înghițire și de pătrundere în căile respiratorii. H225 - Lichid și vapori foarte inflamabili. H319 - Provoacă o iritare gravă a ochilor. P101 Dacă este necesară consultarea medicului, țineți la îndemână recipientul sau eticheta produsului. P102 A nu se lăsa la îndemâna copiilor. P210 A se păstra departe de surse de căldură, suprafețe fierbinți, scânteii, flăcări și alte surse de aprindere. Fumatul interzis.

- max 15%. Apply with brush, roller or spray at a temperature of between 13⁰C - 30⁰C and humidity max. 80%.

Available after mixing: 6-10 hours.

Drying time (20⁰-25⁰C):

On the surface: 4 hours / for repainting: 4 hours – 7 days / final drying: 7 days.

Then apply DUROFLOOR COAT.

WARNING: The finishing coat after DUROFLOOR PRIMER is applied after a minimum of 4 hours and max. 7 days.

SHELF LIFE: 12 months from the date of manufacture marked on the packaging under the conditions of storage. Store in areas protected from fire, frost and direct sunlight.

Product built into Quality Management System - Environment - Operational Health and Safety System in accordance with ISO 9001/2018, 14001/2018 and OHSAS 18001/2018.

Hazard statements and precautions:

H315 - Causes skin irritation. Skin Sens. 1: H317 - May cause an allergic skin reaction. H373 - May cause organ damage in case of prolonged or repeated exposure. H361d - Susceptible to harm to the fetus. H412 - Harmful to aquatic life, with long-term effects. H304 - May be fatal if swallowed and enters airways. H225 - Highly flammable liquid and vapor. H319 - Causes serious eye irritation.

P101 If medical advice is required, keep the container or the label of the product at hand. P102 Keep out of the reach of children. P210 Keep away from sources



PRODUCĂTOR/ PRODUCER:
S.C. COSTHEVA S.R.L. - CHEMICALS - GASES - PAINTS
STR. CAPITAN PAPADOPOL NR. 14
CONSTANTA, ROMANIA
Tel.: 0241.62.54.05
office@costheva.com www.costheva.com



P264 Spălați-vă bine după utilizare. P280 Purtați mănuși de protecție/îmbrăcăminte de protecție/echipament de protecție a ochilor/ echipament de protecție a feței. P305+P351+P338 ÎN CAZ DE CONTACT CU OCHII: Clătiți cu atenție cu apă timp de mai multe minute. Scoateți lentilele de contact, dacă este cazul și dacă acest lucru se poate face cu ușurință. Continuați să clătiți. P370+P378 în caz de incendiu: A se utiliza stingătorul cu praf ABC pentru a stinge. P501 Aruncați conținutul/recipientul în conformitate cu sistemul de colectare selectivă aplicat în municipiul dvs..

Substanțe care contribuie la clasificare: Epichlorohydrin/Bisphenol-A epoxy resin (700 < MW < 1100) (CAS 25036-25-3); Phenol, methylstyrenated (CAS 68512-30-1); Toluene (CAS 108-88-3); Etilbenzen (CAS 100-41-4)

AMBALARE: 1kg, 5 kg, 10 kg si 20 kg

of heat, hot surfaces, sparks, flames and other sources of ignition. Smoking prohibited. P264 Wash thoroughly after use. P280 Wear protective gloves / protective clothing / eye protection / face protection. P305 + P351 + P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove the contact lenses, if necessary, and if this can be done easily. Continue to rinse. P370 + P378 in case of fire: Use extinguisher ABC to extinguish. P501 Discard the contents / container according to the selective collection system applied in your municipality.

Substances which contribute to the classification: Epichlorohydrin / Bisphenol-A epoxy resin (700 <MW <1100) (CAS 25036-25-3); Phenol, methylstyrenated (CAS 68512-30-1); Toluene (CAS 108-88-3); Ethylbenzene (CAS 100-41-4)

PACKAGING: 1kg, 5kg, 10kg and 20kg



PRODUCĂTOR/ PRODUCER:
S.C. COSTHEVA S.R.L. - CHEMICALS - GASES - PAINTS
STR. CAPITAN PAPADOPOL NR. 14
CONSTANTA, ROMANIA
Tel.: 0241.62.54.05
office@costheva.com www.costheva.com

